

SIL-580 XM+ **BIFACIAL**



SIL SOLAR

NEXT-GENERATION N-TYPE CELL TECHNOLOGY

Manufactured exclusively in the USA.


 (\mathbf{H})

TEC

- Improved Shade Tolerance
- Efficient Bifacial Energy Yield
- Increased Performance in **High Temperatures**
- Improved Low-Light Performance
 Enhanced Durability Reduced Degradation Rate

CE

• 25-Year Product Warranty/ 30-Year Performance Warranty



ELECTRICAL SPECIFICATIONS			580		
Test Conditions		STC	BSTC	NOCT	
Module Power (Pmax)	Wp	580	632.8	428.2	
Maximum power voltage (Vpmax)	V	44.27	44.27	40.73	
Maximum power current (Ipmax)	A	13.10	14.29	10.51	
Open circuit voltage (Voc)	V	52.27	52.32	48.08	
Short circuit current (Isc)	A	13.85	15.11	11.12	
Module efficiency	%	22.4%			
Maximum system voltage (VDC)	V	1500			
Series fuse rating	А	30			
Power Tolerance	Wp	0 to +10			
Bifaciality Factor	%	80±5			


Performance conditions: Measurement tolerance ≤ 3% • Standard Test Conditions (STC): 1000 W/m², AM 1.5, Temperature 25 °C • Nominal Operating Cell Temperature (NOCT): 800 W/m², AM 1.5 • Bifacial Standard Test Conditions (BSTC): 1000 W/m² + ϕ × 135 W/m², ϕ = 80 %, AM 1.5 • Electrical characteristics may vary by ±5%.

MECHANICAL PROPERTIES / COMPONENTS		METRIC		IMPERIAL	
Module weight		28.5 kg ±0.2 kg		62.8 lbs ±0.4 lbs	
Dimensions (H x L x D)		2278 mm x 1133 mm x 35 mm		89.7 in x 44.6 in x 1.4 in	
Maximum surface load (wind/snow)*		2400 Pa rear load / 5400 Pa front load		50.1 lb/ft² rear load / 112.8 lb/ft² front load	
Hail impact resistance		ø 25 mm at 83 km/h		ø 1 in at 51.6 mph	
Cells		144 Half cells - N-Type Silicon solar cell 182 mm x 91 mm		144 Half cells - N-Type Silicon solar cell 7.16 in x 3.58 in	
Glass		3.2 mm high transmittance, tempered, anti-reflective coating		0.126 in high transmittance, tempered, anti-reflective coating	
Cables and connectors (refer to installation manual)		1350 mm, ø 5.7 mm, EVO2 from Staubli		53.1 in, ø 0.22 in (12 AWG), EVO2 from Staubli	
Backsheet		High durability, superior hydrolysis and UV resistance, multi-layer dielectric film, transparent PV backsheet			
Frame		Anodized Aluminum (Silver)			
Junction Box		UL 3730 Certified, IEC 62790 Certified, IP68 rated, 3 diodes			
TEMPERATURE RATINGS		WARRANTIES			
Temperature Coefficient Isc	0.04 %/°C		Module product workmanship warranty		25 years**
Temperature Coefficient Voc	-0.24 %/°C		Linear power performance guarantee		30 years
Temperature Coefficient Pmax NOCT (± 2°C)	-0.29 %/°C 45 °C				≥ 98% end 1st yr ≥ 94.7% end 12th yr ≥ 90.8% end 25th yr
Operating temperature	-40/+85 °C				≥ 89.3% end 30th yr

CERTIFICATIONS	SHIPPING SPECS		
Product	UL 61215, UL 61730, CSA C22.2#61730, IEC 61215, IEC 61730, IEC 61701 (Salt Mist Corrosion), IEC 62716 (Ammonia Corrosion), CEC Listed,	Modules Per Pallet:	29
	UL Fire Rating: Type 1	California (Pallets per load)	21
Factory	ISO9001:2015	Others (Pallets per load)	22

A Warning. Read the Safety and Installation Manual for mounting specifications and before handling, installing and operating modules.
 12 year extendable to 25 years subject to registration and conditions outlined under "Warranty" at silfabsolar.com.

Certification and CEC listing in progress.



SILFAB SOLAR INC.

1770 Port Drive Burlington WA 98233 USA **T** +1 360.569.4733 info@silfabsolar.com SILFABSOLAR.COM

7149 Logistics Lane Fort Mill SC 29715 USA **T** +1 839.400.4338

240 Courtneypark Drive East Mississauga ON L5T 2S5 Canada T +1 905.255.2501 F +1 905.696.0267

Silfab - SIL-580-XM+-BIFACIAL 20250106

No reproduction of any kind is allowed without permission. Data and information is subject to modifications without notice. \otimes Silfab Solar inc., 2024. Silfab Solar[®] is a registered trademark of Silfab Solar Inc.

PAN files generated from 3rd party performance data are available for download at: silfabsolar.com/downloads.